

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re patent application of:)
 Ernest De Ruiter) Before the Examiner
 Serial No. 10/567,794) Not Yet Assigned
 Filed February 9, 2006) Group Art Unit ____
 ACTIVATED CHARCOAL) January 7, 2008
 PRODUCTION)

I hereby certify that this correspondence is being electronically filed with the United States Patent and Trademark Office as a Designated/Elected Office of the PCT on

January 7, 2008

(Date of Deposit)

James M. Durlacher

Name of Registered Representative

James M. Durlacher
 Signature

January 7, 2008

Date of Signature

REQUEST TO WITHDRAW
HOLDING OF ABANDONMENT

Commissioner for Patents
 P. O. Box 1450
 Alexandria, VA 22313-1450
BOX PCT
 Sir:

The above-captioned patent application was forwarded to the U.S. Patent and Trademark Office, acting as a Designated/Elected Office of the PCT, on February 9, 2006 by Express Mail. A Notification of Missing Requirements Under 35 U.S.C. 371 in the United States Designated/Elected Office (DO/EO/US) was issued August 11, 2006. A Response was timely filed and mailed to the U.S. PTO by Express Mail on September 18, 2006 (see enclosed copy) and received by the U.S. PTO as of September 18, 2006 (see copy of returned postal card). However, a Notification of Abandonment was issued by the United States Patent and Trademark Office on December 11, 2007 (copy enclosed).

Applicant hereby respectfully requests and petitions that the holding of abandonment be withdrawn for the above-identified patent application.

Although the Response to the Notification of Missing Requirements was timely filed, there is no record of the Response having been processed by the US PTO. The Response to the Notification of Missing Requirements is not listed on the "available documents" listing from the Patent and Trademark Office (see enclosed copy).

Applicant's Attorney submitted a Request for Filing Receipt and enclosed a copy of the returned postal card from the filing of the Response to Missing Requirements on May 9, 2007. No action was taken by the U.S. PTO other than to abandon this application.

Therefore, reinstatement of the subject patent application is respectfully requested.

Although no fee is believed to be due in order to reinstate the subject patent application, please charge any fees that are due to Deposit Account No. 23-3030.

Respectfully submitted,

By James M. Durlacher
James M. Durlacher, Reg. No. 28,840
Woodard, Emhardt, Moriarty,
McNett & Henry LLP
111 Monument Circle, Suite 3700
Indianapolis, Indiana 46204-5137
(317) 634-3456



UNITED STATES PATENT AND TRADEMARK OFFICE

UNITED STATES DEPARTMENT OF COMMERCE
United States Patent and Trademark Office
Address: COMMISSIONER FOR PATENTS
P.O. Box 1450
Alexandria, Virginia 22313-1450
www.uspto.gov

U.S. APPLICATION NUMBER NO. 10/567,794	FIRST NAMED APPLICANT Ernest De Ruiter	ATTY. DOCKET NO. 8312-7/05.1816.6.do
30565 WOODARD, EMHARDT, MORIARTY, MCNETT & HENRY LLP 111 MONUMENT CIRCLE, SUITE 3700 INDIANAPOLIS, IN 46204-5137		INTERNATIONAL APPLICATION NO. PCT/EP04/08314
		I.A. FILING DATE 07/24/2004
		PRIORITY DATE 08/11/2003

RECEIVED

DEC 14 2007

CONFIRMATION NO. 2686

371 ABANDONMENT/TERMINATION
LETTER



Date Mailed: 12/11/2007

Woodard, Emhardt, Moriarty,
McNett & Henry, LLP

NOTIFICATION OF ABANDONMENT

The United States Patent and Trademark Office in its capacity as a Designated / Elected Office (37 CFR 1.495) has made the following determination:

- Applicant has failed to respond to the notification of MISSING REQUIREMENTS (Form PCT/DO/EO/905), mailed 08/11/2006 within the time period set therein.

Therefore, the above identified application failed to meet the requirements of 35 U.S.C. 371 and 37 CFR 1.495, and is ABANDONED AS TO THE UNITED STATES OF AMERICA.

DONNA S GREENE

Telephone: (703) 308-9140 EXT 222

Attorney Docket No. 8312-7

Initials 8:ss JMD

PATENT PROSECUTION

Date 09/18/06

Application/Patent No. 10/567,794

File/Issue Date IA Filing Date: July 24, 2004

Applicant Ernest de RUITER

Title ACTIVATED CHARCOAL PRODUCTION

- ☒ Return Receipt Postcard
☒ Transmittal Form PTO/SB/21
☒ Fee Transmittal Form PTO/SB/17
☒ Credit Card Form PTO-2038 \$130.00
☐ Response to Notice of Missing Parts
☐ Amendment/Response to Office Action
☐ Petition for Extension of Time PTO/SB/22
☐ Application Data Sheet
☐ Declaration Form PTO/SB/ - -
pages
☐ Assignment Recordation Form PTO-1595
☐ Assignment Documents - - pages

- ☐ Power of Attorney Form PTO/SB/80
☐ Power of Attorney/Corresp. Form
PTO/SB/81
☐ CFR 3.73(b) Statement Form PTO/SB/36
☐ Information Disclosure Statement Cover Pg.
☐ Information Disclosure Statement Form
PTO/SB/08 - - page(s) with # -
enclosed references.
☒ Response to Notification of Missing
Requirements
☒ Copy of Notice of Missing Requirements
☒ English translation of original PCT text
☒ English translation of Amended claims.

RECEIPT OF THE ATTACHED IS HEREBY ACKNOWLEDGED

#419720

EV579027655US

COPY



United States Patent and Trademark Office

[Home](#) | [Site Index](#) | [Search](#) | [FAQ](#) | [Glossary](#) | [Guides](#) | [Contacts](#) | [eBusiness](#) | [eBiz Alerts](#) | [News](#) | [Help](#)
[Portal Home](#) | [Patent](#) | [Trademark](#) | [Other](#) | [Sign-Off](#) [Authenticated Session](#)

Patent eBusiness

- [Electronic Filing](#)
- [Patent Application Information \(PAIR\)](#)
- [Patent Ownership](#)
- [Fees](#)
- [Supplemental Resources & Support](#)

Patent Information

- [Patent Guidance and General Info](#)
- [Codes, Rules & Manuals](#)
- [Employee & Office Directories](#)
- [Resources & Public Notices](#)

Patent Searches

- [Patent Official Gazette](#)
- [Search Patents & Applications](#)
- [Search Biological Sequences](#)
- [Copies, Products & Services](#)

Other

- [Copyrights](#)
- [Trademarks](#)
- [Policy & Law Reports](#)

Secured Patent Application Information Retrieval

[Download](#) [Order Certified Application As Filed](#) [Order Certified File Wrapper](#) [View](#)

10/567,794 Activated Charcoal Production

Select New Case	Application Data	Transaction History	Image File Wrapper	Continuity Data	Foreign Priority	Address & Attorney/Agent	Assignments	Display References	Publication Review
-----------------	------------------	---------------------	--------------------	-----------------	------------------	--------------------------	-------------	--------------------	--------------------

This application is officially maintained in electronic form. To View: Click the desired Document Description. To Download and Print: Check the desired document(s) and click Start Download.

Available Documents

Mail Room Date	Document Code	Document Description	Document Category	Page Count
05-09-2007	LET.	Miscellaneous Incoming Letter	PROSECUTION	
08-11-2006	M905	Notice of DO/EO Missing Requirements Mailed Information	PROSECUTION	
04-25-2006	IDS	Disclosure Statement (IDS) Filed	PROSECUTION	
04-25-2006	NPL	NPL Documents	PRIOR ART	
02-09-2006	TRNA	Transmittal of New Application	PROSECUTION	
02-09-2006	SPEC	Specification Drawings-only	PROSECUTION	
02-09-2006	DRW	black and white line drawings	PROSECUTION	
02-09-2006	OATH	Oath or Declaration filed	PROSECUTION	
02-09-2006	WFEE	Fee Worksheet (PTO-06) Information	PROSECUTION	
02-09-2006	IDS	Disclosure Statement (IDS) Filed	PROSECUTION	
02-09-2006	FOR	Foreign Reference	PRIOR ART	
02-09-2006	FOR	Foreign Reference	PRIOR ART	
02-09-2006	FOR	Foreign Reference Documents submitted with 371 Applications	PRIOR ART	
02-09-2006	371P		PROSECUTION	

02-09-2006	371P	Documents submitted with 371 Applications	PROSECUTION
02-09-2006	371P	Documents submitted with 371 Applications	PROSECUTION
02-09-2006	371P	Documents submitted with 371 Applications	PROSECUTION
02-09-2006	371P	Documents submitted with 371 Applications	PROSECUTION
02-09-2006	ABST	Abstract	PROSECUTION
02-09-2006	371P	Documents submitted with 371 Applications	PROSECUTION
02-09-2006	371P	Documents submitted with 371 Applications	PROSECUTION
02-09-2006	ABST	Abstract	PROSECUTION
02-09-2006	FRPR	Certified Copy of Foreign Priority Application	PROSECUTION
02-09-2006	FRPR	Certified Copy of Foreign Priority Application	PROSECUTION
02-09-2006	371P	Documents submitted with 371 Applications	PROSECUTION

[Select ALL](#) [Clear](#)

If you need help:

- Call the Patent Electronic Business Center at (866) 217-9197 (toll free) or e-mail EBC@uspto.gov for specific questions about Patent Application Information Retrieval
- Send general questions about USPTO programs to the [USPTO Contact Center \(UCC\)](#)
- If you experience technical difficulties or problems with this application, please rep e-mail to [Electronic Business Support](#) or call 1 800-786-9199.

You can suggest USPTO webpages or material you would like featured on this section by E-mail to the webmaster@uspto.gov. While we cannot promise to accommodate all requests, they will be considered and may lead to other improvements on the website.

[Home](#) | [Site Index](#) | [Search](#) | [eBusiness](#) | [Help](#) | [Privacy Policy](#)

TO: Auto-reply fax to 317 637 7561 COMPANY:

Auto-Reply Facsimile Transmission



TO:

Fax Sender at 317 637 7561

Fax Information

Date Received:

5/9/2007 11:09:04 AM [Eastern Daylight Time]

Total Pages:

3 (including cover page)

ADVISORY: This is an automatically generated return receipt confirmation of the facsimile transmission received by the Office. Please check to make sure that the number of pages listed as received in Total Pages above matches what was intended to be sent. Applicants are advised to retain this receipt in the unlikely event that proof of this facsimile transmission is necessary. Applicants are also advised to use the certificate of facsimile transmission procedures set forth in 37 CFR 1.8(a) and (b), 37 CFR 1.6(f). Trademark Applicants, also see the Trademark Manual of Examining Procedure (TMEP) section 306 et seq.

Received
Cover
Page
=====>

MAY/09/2007/FEB 11:09 AM WOODARD EMHARDT		FAX No. 317 637 7561		P. 001															
WENIMH/SB/21 (4/03)																			
TRANSMITTAL FORM			<table border="1"> <tr> <td>Application Number</td> <td>10/567,794</td> </tr> <tr> <td>Filing Date</td> <td>July 24, 2004 (Init Filing Date)</td> </tr> <tr> <td>First Named Inventor</td> <td>Ernest de RUITER</td> </tr> <tr> <td>Group Art Unit</td> <td>Not Yet Assigned</td> </tr> <tr> <td>Examiner Name</td> <td>Not Yet Assigned</td> </tr> <tr> <td>Total Number of Pages in this Submission</td> <td>3</td> </tr> <tr> <td>Attorney Docket Number</td> <td>8312-7</td> </tr> </table>			Application Number	10/567,794	Filing Date	July 24, 2004 (Init Filing Date)	First Named Inventor	Ernest de RUITER	Group Art Unit	Not Yet Assigned	Examiner Name	Not Yet Assigned	Total Number of Pages in this Submission	3	Attorney Docket Number	8312-7
Application Number	10/567,794																		
Filing Date	July 24, 2004 (Init Filing Date)																		
First Named Inventor	Ernest de RUITER																		
Group Art Unit	Not Yet Assigned																		
Examiner Name	Not Yet Assigned																		
Total Number of Pages in this Submission	3																		
Attorney Docket Number	8312-7																		
<table border="1"> <tr> <th colspan="3">ENCLOSURES (check all that apply)</th> </tr> <tr> <td> <input type="checkbox"/> Fee Transmittal Form <input type="checkbox"/> Fee Attached see PTO-2038 form <input type="checkbox"/> Amendment Response <input type="checkbox"/> After Final <input type="checkbox"/> Affidavit/Declaration(s) <input type="checkbox"/> Extension of Time Request <input type="checkbox"/> Express Abandonment Request <input type="checkbox"/> Information Disclosure Statement <input type="checkbox"/> Certified Copy of Priority Documents <input type="checkbox"/> Response to Missing Parts/Incomplete Application <input type="checkbox"/> Response to Missing Parts under 37 CFR 1.52 or 1.63 </td> <td> <input type="checkbox"/> Assignment Papers <input type="checkbox"/> Drawing(s) <input type="checkbox"/> Licensing-related Papers <input type="checkbox"/> To Convert a Provisional Application <input type="checkbox"/> Power of Attorney, and Correspondence Address Form <input type="checkbox"/> Terminal Disclaimer <input type="checkbox"/> Small Entity Statement <input type="checkbox"/> Request for Refund </td> <td> <input type="checkbox"/> After Allowance Communication to Group <input type="checkbox"/> Appeal Communication to Board of Appeals and Interferences <input type="checkbox"/> Appeal Communication to Group (Appeal Notice, Brief, Reply Brief) <input type="checkbox"/> Proprietary Information <input type="checkbox"/> Status Letter <input checked="" type="checkbox"/> Additional Enclosure (Please Identify below) <input type="checkbox"/> Return Receipt Postcard Request for Filing Receipt; Copy of returned postal card from Response to Missing Requirements </td> </tr> <tr> <td colspan="3">Remarks</td> </tr> </table>						ENCLOSURES (check all that apply)			<input type="checkbox"/> Fee Transmittal Form <input type="checkbox"/> Fee Attached see PTO-2038 form <input type="checkbox"/> Amendment Response <input type="checkbox"/> After Final <input type="checkbox"/> Affidavit/Declaration(s) <input type="checkbox"/> Extension of Time Request <input type="checkbox"/> Express Abandonment Request <input type="checkbox"/> Information Disclosure Statement <input type="checkbox"/> Certified Copy of Priority Documents <input type="checkbox"/> Response to Missing Parts/Incomplete Application <input type="checkbox"/> Response to Missing Parts under 37 CFR 1.52 or 1.63	<input type="checkbox"/> Assignment Papers <input type="checkbox"/> Drawing(s) <input type="checkbox"/> Licensing-related Papers <input type="checkbox"/> To Convert a Provisional Application <input type="checkbox"/> Power of Attorney, and Correspondence Address Form <input type="checkbox"/> Terminal Disclaimer <input type="checkbox"/> Small Entity Statement <input type="checkbox"/> Request for Refund	<input type="checkbox"/> After Allowance Communication to Group <input type="checkbox"/> Appeal Communication to Board of Appeals and Interferences <input type="checkbox"/> Appeal Communication to Group (Appeal Notice, Brief, Reply Brief) <input type="checkbox"/> Proprietary Information <input type="checkbox"/> Status Letter <input checked="" type="checkbox"/> Additional Enclosure (Please Identify below) <input type="checkbox"/> Return Receipt Postcard Request for Filing Receipt; Copy of returned postal card from Response to Missing Requirements	Remarks							
ENCLOSURES (check all that apply)																			
<input type="checkbox"/> Fee Transmittal Form <input type="checkbox"/> Fee Attached see PTO-2038 form <input type="checkbox"/> Amendment Response <input type="checkbox"/> After Final <input type="checkbox"/> Affidavit/Declaration(s) <input type="checkbox"/> Extension of Time Request <input type="checkbox"/> Express Abandonment Request <input type="checkbox"/> Information Disclosure Statement <input type="checkbox"/> Certified Copy of Priority Documents <input type="checkbox"/> Response to Missing Parts/Incomplete Application <input type="checkbox"/> Response to Missing Parts under 37 CFR 1.52 or 1.63	<input type="checkbox"/> Assignment Papers <input type="checkbox"/> Drawing(s) <input type="checkbox"/> Licensing-related Papers <input type="checkbox"/> To Convert a Provisional Application <input type="checkbox"/> Power of Attorney, and Correspondence Address Form <input type="checkbox"/> Terminal Disclaimer <input type="checkbox"/> Small Entity Statement <input type="checkbox"/> Request for Refund	<input type="checkbox"/> After Allowance Communication to Group <input type="checkbox"/> Appeal Communication to Board of Appeals and Interferences <input type="checkbox"/> Appeal Communication to Group (Appeal Notice, Brief, Reply Brief) <input type="checkbox"/> Proprietary Information <input type="checkbox"/> Status Letter <input checked="" type="checkbox"/> Additional Enclosure (Please Identify below) <input type="checkbox"/> Return Receipt Postcard Request for Filing Receipt; Copy of returned postal card from Response to Missing Requirements																	
Remarks																			
SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT																			
Firm or Individual Name	James M. Durlacher Woodard, Emhardt, Moriarty, McNeit & Henry LLP																		
Signature	<i>James M. Durlacher</i>																		
Date	May 9, 2007																		
CERTIFICATE OF MAILING																			
I hereby certify that this correspondence is being deposited with the United States Postal Service with sufficient postage so that class mail in an envelope addressed to: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22315-1450, or facsimile transmitted to the U.S. Patent and Trademark Office on: May 9, 2007																			
Name (Print/Type)	James M. Durlacher																		
Signature	<i>James M. Durlacher</i>		Date	May 9, 2007															
8312-7JMD-1-05263-33																			

COPY

PAGE 123 * RCDV AT 5/9/2007 11:09:04 AM [Eastern Daylight Time] * SVR:USPTO-EFAXF-20 * DNS:2738300 * CSID:317 637 7561 * DURATION (mm:ss):01:16

LawBase 5/9/07
Matter No. 8312-7
Routed to *(mp) Sandy*

TRANSACTION REPORT

P.01/01

MAY/09/2007/WED 11:10 AM

FAX(TX)

#	DATE	START T.	RECEIVER	COM.TIME	PAGE	TYPE/NOTE	FILE
001	MAY/09	11:09AM	PTO Central FAX	0:01:05	3	OK	ECM 2577

WEMMH/SB/21 (4/03)

TRANSMITTAL
FORM

(to be used for all correspondence after initial filing)

Application Number	10/567,794
Filing Date	July 24, 2004 (Int'l Filing Date)
First Named Inventor	Ernest de RUITER
Group Art Unit	Not Yet Assigned
Examiner Name	Not Yet Assigned
Total Number of Pages in this Submission	3
Attorney Docket Number	8312-7

ENCLOSURES (check all that apply)

<input type="checkbox"/> Fee Transmittal Form <input type="checkbox"/> Fee Attached see PTO-2038 form <input type="checkbox"/> Amendment Response <input type="checkbox"/> After Final <input type="checkbox"/> Affidavits/declaration(s) <input type="checkbox"/> Extension of Time Request <input type="checkbox"/> Express Abandonment Request <input type="checkbox"/> Information Disclosure Statement <input type="checkbox"/> Certified Copy of Priority Documents <input type="checkbox"/> Response to Missing Parts/ Incomplete Application <input type="checkbox"/> Response to Missing Parts under 37 CFR 1.52 or 1.53	<input type="checkbox"/> Assignment Papers <input type="checkbox"/> Drawing(s) <input type="checkbox"/> Licensing-related Papers <input type="checkbox"/> To Convert a Provisional Application <input type="checkbox"/> Power of Attorney, and Correspondence Address Form <input type="checkbox"/> Terminal Disclaimer <input type="checkbox"/> Small Entity Statement <input type="checkbox"/> Request for Refund	<input type="checkbox"/> After Allowance Communication to Group <input type="checkbox"/> Appeal Communication to Board of Appeals and Interferences <input type="checkbox"/> Appeal Communication to Group (Appeal Notice, Brief, Reply Brief) <input type="checkbox"/> Proprietary Information <input type="checkbox"/> Status Letter <input checked="" type="checkbox"/> Additional Enclosure (please identify below) <input type="checkbox"/> Return Receipt Postcard Request for Filing Receipt; Copy of returned postal card from Response to Missing Requirements
Remarks <div style="text-align: right; font-size: 2em; font-weight: bold;">COPY</div>		

SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT

Firm or Individual Name	James M. Durlacher Woodard, Emhardt, Moriarty, McNett & Henry LLP
Signature	<i>James M. Durlacher</i>
Date	May 9, 2007

CERTIFICATE OF MAILING

I hereby certify that this correspondence is being deposited with the United States Postal Service with sufficient postage as first class mail in an envelope addressed to: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450, or facsimile transmitted to the U.S. Patent and Trademark Office on: May 9, 2007

Name (Print/Type)	James M. Durlacher
Signature	<i>James M. Durlacher</i>
Date	May 9, 2007

TRANSMITTAL FORM

(to be used for all correspondence after initial filing)

TRANSMITTAL FORM (to be used for all correspondence after initial filing)		Application Number	10/567.794
		Filing Date	July 24, 2004 (Int'l Filing Date)
		First Named Inventor	Ernest de RUITER
		Group Art Unit	Not Yet Assigned
		Examiner Name	Not Yet Assigned
Total Number of Pages in this Submission	3	Attorney Docket Number	8312-7

ENCLOSURES (check all that apply)

<input type="checkbox"/> Fee Transmittal Form <input type="checkbox"/> Fee Attached see PTO-2038 form <input type="checkbox"/> Amendment Response <input type="checkbox"/> After Final <input type="checkbox"/> Affidavits/declaration(s) <input type="checkbox"/> Extension of Time Request <input type="checkbox"/> Express Abandonment Request <input type="checkbox"/> Information Disclosure Statement <input type="checkbox"/> Certified Copy of Priority Documents <input type="checkbox"/> Response to Missing Parts/ Incomplete Application <input type="checkbox"/> Response to Missing Parts under 37 CFR 1.52 or 1.53	<input type="checkbox"/> Assignment Papers <input type="checkbox"/> Drawing(s) <input type="checkbox"/> Licensing-related Papers <input type="checkbox"/> To Convert a Provisional Application <input type="checkbox"/> Power of Attorney, and Correspondence Address Form <input type="checkbox"/> Terminal Disclaimer <input type="checkbox"/> Small Entity Statement <input type="checkbox"/> Request for Refund	<input type="checkbox"/> After Allowance Communication to Group <input type="checkbox"/> Appeal Communication to Board of Appeals and Interferences <input type="checkbox"/> Appeal Communication to Group (Appeal Notice, Brief, Reply Brief) <input type="checkbox"/> Proprietary Information <input type="checkbox"/> Status Letter <input checked="" type="checkbox"/> Additional Enclosure (please identify below) <input type="checkbox"/> Return Receipt Postcard Request for Filing Receipt; Copy of returned postal card from Response to Missing Requirements
Remarks		

SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT

Firm or Individual Name	James M. Durlacher Woodard, Emhardt, Moriarty, McNett & Henry LLP
Signature	<i>James M. Durlacher</i>
Date	May 9, 2007

CERTIFICATE OF MAILING

I hereby certify that this correspondence is being deposited with the United States Postal Service with sufficient postage as first class mail in an envelope addressed to: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450, or facsimile transmitted to the U.S. Patent and Trademark Office on: **May 9, 2007**

Name (Print/Type)	James M. Durlacher		
Signature	<i>James M. Durlacher</i>	Date	May 9, 2007

8312-7:JMD:#462663:ss

COPY

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re patent application of:)
 Ernest de RUITER) Before the Examiner
 Serial No. 10/567,794) Not Yet Assigned
 Intl Filing Date: July 24, 2004) Group Art Unit ____
 ACTIVATED CHARCOAL PRODUCTION) May 9, 2007

REQUEST FOR
FILING RECEIPT

Assistant Commissioner for Patents
 Washington, D.C. 20231
 ATTN: PCT
 ATTN: Office of Initial Patent Examination's
 Filing Receipt Corrections

Sir:

This is a request for the official filing receipt for the above-identified patent application.

The application was filed with an unsigned Declaration. A Notification of Missing Requirements was issued under Confirmation No. 2686. A Response to the Notification of Missing Requirements was submitted to the U.S. Patent and Trademark Office by Express Mail on September 18, 2006. Enclosed is a photocopy of the returned postal card evidencing receipt by the US PTO of the Response to the Notification of Missing Requirements on September 18, 2006.

Please issue the official filing receipt and forward it to the undersigned attorney of record as soon as possible.

Respectfully submitted,

By James M. Durlacher
 James M. Durlacher, Reg. No. 28,840
 Woodard, Emhardt, Moriarty,
 McNett & Henry LLP
 111 Monument Circle, Suite 3700
 Indianapolis, Indiana 46204-5137
 (317) 634-3456

I hereby certify that this correspondence is being
 telefaxed to the United States Patent and
 Trademark Office via Fax No. (571)-273-8300

on
 May 9, 2007

(Date of Deposit)

James M. Durlacher

Name of Registered Representative

James M. Durlacher

Signature

May 9, 2007

Date of Signature

COPY

Attorney Docket No. 8312-7

PATENT PROSECUTION

Initials 8:ss JMD

Date 09/18/06

Application/Patent No. 10/567.794

File/Issue Date IA Filing Date: July 24, 2004

Applicant Ernest de RUITER

Title ACTIVATED CHARCOAL PRODUCTION

- ☒ Return Receipt Postcard
☒ Transmittal Form PTO/SB/21
☒ Fee Transmittal Form PTO/SB/17
☒ Credit Card Form PTO-2038 \$130.00
☐ Response to Notice of Missing Parts
☐ Amendment/Response to Office Action
☐ Petition for Extension of Time PTO/SB/22
☐ Application Data Sheet _____
☐ Declaration Form PTO/SB/____ - ____
pages
☐ Assignment Recordation Form PTO-1595
☐ Assignment Documents - ____ pages

- ☐ Power of Attorney Form PTO/SB/80
☐ Power of Attorney/Corresp. Form
PTO/SB/81
☐ CFR 3.73(b) Statement Form PTO/SB/50
☐ Information Disclosure Statement Cover Pg.
☐ Information Disclosure Statement Form
PTO/SB/08 - ____ page(s) with ____
enclosed references
☒ Response to Notification of Missing
Requirements
☒ Copy of Notice of Missing Requirements
☒ English translation of original PCT text
☒ English translation of Amended claims

RECEIPT OF THE ATTACHED IS HEREBY ACKNOWLEDGED

#419720

EV579027655US

COPY

TRANSMITTAL FORM

(to be used for all correspondence after initial filing)

Application Number	10/567.794	
	Filing Date	I.A. Filing Date: July 24, 2004
	First Named Inventor	Ernest de RUITER
	Group Art Unit	Not Yet Assigned
	Examiner Name	Not Yet Assigned
Total Number of Pages in this Submission	Attorney Docket Number	8312-7/ 05.1816.6.do

ENCLOSURES (check all that apply)

<input checked="" type="checkbox"/> Fee Transmittal Form <input checked="" type="checkbox"/> Fee Attached see PTO-2038 form <input type="checkbox"/> Amendment Response <input type="checkbox"/> After Final <input type="checkbox"/> Affidavits/declaration(s) <input type="checkbox"/> Extension of Time Request <input type="checkbox"/> Express Abandonment Request <input type="checkbox"/> Information Disclosure Statement <input type="checkbox"/> Certified Copy of Priority Documents <input type="checkbox"/> Response to Missing Parts/ Incomplete Application <input type="checkbox"/> Response to Missing Parts under 37 CFR 1.52 or 1.53	<input type="checkbox"/> Assignment Papers <input type="checkbox"/> Drawing(s) <input type="checkbox"/> Licensing-related Papers <input type="checkbox"/> To Convert a Provisional Application <input type="checkbox"/> Power of Attorney, Revocation, Change of Correspondence Address <input type="checkbox"/> Terminal Disclaimer <input type="checkbox"/> Small Entity Statement <input type="checkbox"/> Request for Refund	<input type="checkbox"/> After Allowance Communication to Group <input type="checkbox"/> Appeal Communication to Board of Appeals and Interferences <input type="checkbox"/> Appeal Communication to Group (Appeal Notice, Brief, Reply Brief) <input type="checkbox"/> Proprietary Information <input type="checkbox"/> Status Letter <input checked="" type="checkbox"/> Additional Enclosure (please identify below) <input checked="" type="checkbox"/> Return Receipt Postcard Response to Notification of Missing Requirements under 35 U.S.C. §371; Copy of Notice of Missing Requirements 371 Formalities Itr No. 2686; English translation of original PCT filing text; & English translation of Amended claims.
Remarks		

SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT

Firm or Individual Name	James M. Durlacher Woodard, Emhardt, Moriarty, McNett & Henry LLP
Signature	<i>James M. Durlacher</i>
Date	September 18, 2006

Certificate of Mailing

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR §1.10 on the date indicated above and is addressed to Mail Stop PCT, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.			
on this date: September 18, 2006			
Typed or printed name	Sandra L. Stilz		
Signature	<i>Sandra L. Stilz</i>	Date	September 18, 2006

COPY

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

United States Patent and Trademark Office
Credit Card Payment Form
Please Read Instructions before Completing this Form

Credit Card Information			
Credit Card Type: <input type="checkbox"/> Visa <input type="checkbox"/> MasterCard <input checked="" type="checkbox"/> American Express <input type="checkbox"/> Discover			
Credit Card Account #: 3782-966669-91276		Security Code: 4143	
Credit Card Expiration Date: 04/10			
Name as it Appears on Credit Card: J M DURLACHER			
Payment Amount \$ (US Dollars): \$130.00			
Cardholder Signature: <i>JM Durlacher</i>		Date: September 18, 2006	
<p>Refund Policy: The USPTO may refund a fee paid by mistake or in excess of that required. A change of purpose after the payment of a fee will not entitle a party to a refund of such fee. The office will not refund amounts of \$25.00 or less unless a refund is specifically requested, and will not notify the payor of such amounts (37 CFR 1.26). Refund of a fee paid by credit card will be issued as a credit to the credit card account to which the fee as charged.</p> <p>Services Charge: There is a \$50.00 service charge for processing each payment refused (including a check returned "unpaid") or charged back by a financial institution (37 CFR 1.21(m)).</p>			
Credit Card Information			
Street Address 1: 111 Monument Circle			
Street Address 2:			
City: Indianapolis			
State/Province: Indiana		Zip/Postal Code: 46204	
Country: USA			
Daytime Phone #: 317-634-3456		Fax #: 317-637-7561	
Request and Payment Information			
Description of Request and Payment Information: Fee for Submission of Missing Requirements (English translation)			
<input checked="" type="checkbox"/> Patent Fee	<input type="checkbox"/> Patent Maintenance Fee	<input type="checkbox"/> Trademark Fee	<input type="checkbox"/> Other Fee
Application No. 10/567,794	Application No.	Application No.	IDON Customer No.
Patent No.	Patent No.	Registration No.	
Attorney Docket No. 8312-7		Identify or Describe Mark	

If the cardholder includes a credit card number on any form or document other than the Credit Card Payment Form, the United States Patent and Trademark Office will not be liable in the event that the credit card number becomes public knowledge.

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Fees pursuant to the Consolidated Appropriations Act, 2005 (H.R. 4818).

**FEE TRANSMITTAL
For FY 2006****Complete if Known**

Application Number	10/567,794
Filing Date	I.A. Filing Date: July 24, 2004
First Named Inventor	Ernest de RUITER
Examiner Name	Not Yet Assigned
Art Unit	Not Yet Assigned
Attorney Docket No.	8312-7/05.1816.6.DO

☒ Applicant claims small entity status. See 37 CFR 1.27

TOTAL AMOUNT OF PAYMENT (\$130.00)

METHOD OF PAYMENT (check all that apply)

- ☐ Check ☒ Credit Card ☐ Money Order ☐ None ☐ Other (please identify): _____
- ☒ Deposit Account Deposit Account number: 23-3030 Deposit Account Name: Woodard, Emhardt, Moriarty, McNett & Henry LLP
For the above-identified deposit account, the Director is hereby authorized to: (check all that apply)
- ☐ Charge fee(s) indicated below ☐ Charge fee(s) indicated below, except for the filing fee
- ☒ Charge any additional fee(s) or underpayments of fee(s) under 37 CFR 1.16 and 1.17. ☒ Credit any overpayments.

WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

FEE CALCULATION**1. BASIC FILING, SEARCH, AND EXAMINATION FEES**

Application Type	FILING FEES		SEARCH FEES		EXAMINATION FEES		Fees Paid (\$)
	Small Entity	Small Entity	Small Entity	Small Entity	Small Entity	Small Entity	
Utility	Fee (\$)	Fee (\$)	Fee (\$)	Fee (\$)	Fee (\$)	Fee (\$)	
Design	300	150	500	250	200	100	0
Plant	200	100	100	50	130	65	
Reissue	200	100	300	150	160	80	
Provisional	300	150	500	250	600	300	
	200	100	0	0	0	0	

2. EXCESS CLAIM FEES**Fee Description**

Each claim over 20 (including Reissues)

Each independent claim over 3 (including Reissues)

Multiple dependent claims

Small Entity	Small Entity
Fee (\$)	Fee (\$)
50	25
200	100
360	180

Multiple Dependent Claims

Total Claims	Extra Claims	Fee (\$)	Fee Paid (\$)
* -20 or HP	= *	x 50	=0

HP = highest number of total claims paid for, if greater than 20

Independent Claims	Extra Claims	Fee (\$)	Fee Paid (\$)
* -3 or HP	= 0	x 200	=0

HP = highest number of independent claims paid for, if greater than 3

3. APPLICATION SIZE FEE

If the specification and drawings exceed 100 sheets of paper (excluding electronically filed sequence or computer listings under 37 CFR 1.52(e)), the application size fee due is \$250 (\$125 for small entity) for each additional 50 sheets or fraction thereof. See 35 U.S.C. 41(a)(1)(G) and 37 C.F.R. 1.16(s).

Total Sheets	Extra Sheets	Number of each additional 50 or fraction thereof	Fee (\$)	Fee Paid (\$)
-100	=	/50 =	(round up to a whole number) x	0

4. OTHER FEE(S)

Late filing of English Translation of original PCT filing text

Fee Paid (\$)
130.00

SUBMITTED BY

Signature	<u>James M. Durlacher</u>	Registration No.	28,840	Telephone	(317) 634-3456
Name (Print/Type)	James M. Durlacher	(Attorney/Agent)		Date	September 18, 2006

Express Mail Label No. EV 579027655 US

DATE OF DEPOSIT: September 18, 2006

I hereby certify that this paper is being deposited with the United States Postal Service "Express-Mail Post Office to Addressee" service under 37 CFR Section 1.10 on the date indicated above and is addressed to the Commissioner for Patents, PO Box 1450, Alexandria, VA, 22313-1450.

Sandra L. Aul
Signature of person mailing paper or fee

8312-7:JMD#419710:ss

COPY

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re patent application of:)
 Ernest de RUITER) Before the Examiner
)
) (Not Yet Assigned)
 Serial No.: 10/567,794)
) Group Art Unit _____
 I.A. Filing Date: July 24, 2004)
) September 18, 2006
Metal Cluster Nano-Compounds)
For Treating Tumor Diseases)

I hereby certify that this correspondence is being
 mailed via Express Mail to the United States
 Patent and Trademark on

on
 September 18, 2006

(Date of Deposit)

James M. Durlacher

Name of Registered Representative

James M. Durlacher
 Signature

September 18, 2006

Date of Signature

RESPONSE TO NOTIFICATION OF MISSING REQUIREMENTS
UNDER 35 U.S.C. §371

Mail Stop PCT

Commissioner for Patents

P. O. Box 1450

Arlington, VA 22313-1450

Sir:

In response to the Notification of Missing Requirements under 35 U.S.C. §371

which has been received for the above application, Applicant submits herewith the
 following documents:

1. An English translation of the original PCT filing text (22 pages);
2. A copy of the English translation of Amended Claims 1-17 of April 1,
 2005 filed on behalf of International Preliminary Examination (4 pages);
4. A copy of the Notice of Missing Requirements;
5. Fee transmittal form; and
6. Credit Card authorization form (PTO-2038).

The fee of \$130 reflecting the small entity surcharge for filing the English
 translation later than the filing date should be charged to the American Express Account

COPY

number shown on the enclosed form. Additionally, please provide any extensions of time which are required and charge any additional fees which are due to Deposit Account No. 23-3030.

Respectfully submitted,

By James M. Durlacher
James M. Durlacher, Reg. No. 28,840
Woodard, Emhardt, Moriarty,
McNett & Henry LLP
Bank One Center/Tower
111 Monument Circle, Suite 3700
Indianapolis, Indiana 46204-5137
(317) 634-3456

COPY



UNITED STATES PATENT AND TRADEMARK OFFICE

UNITED STATES DEPARTMENT OF COMMERCE
United States Patent and Trademark Office
Address: COMMISSIONER FOR PATENTS
P.O. Box 1450
Alexandria, Virginia 22313-1450
www.uspto.gov

U.S. APPLICATION NUMBER NO.	FIRST NAMED APPLICANT	ATTY. DOCKET NO.
10/567,794	Ernest De Ruiter	8312-7/05.1816.6.do

INTERNATIONAL APPLICATION NO.

PCT/EP04/08314

LA. FILING DATE

PRIORITY DATE

07/24/2004

08/11/2003

30565

WOODARD, EMHARDT, MORIARTY, MCNETT & HENRY LLP
111 MONUMENT CIRCLE, SUITE 3700
INDIANAPOLIS, IN 46204-5137

RECEIVED

AUG 18 2006

Woodard, Emhardt, Moriarty,
McNett & Henry, LLP

Date Mailed: 08/11/2006

CONFIRMATION NO. 2686

371 FORMALITIES LETTER




OC000000019983180

NOTIFICATION OF MISSING REQUIREMENTS UNDER 35 U.S.C. 371 IN THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US)

The following items have been submitted by the applicant or the IB to the United States Patent and Trademark Office as a Designated / Elected Office (37 CFR 1.495).

- Indication of Small Entity Status
- Copy of the International Application filed on 02/09/2006
- Copy of the International Search Report filed on 02/09/2006
- Copy of IPE Report filed on 02/09/2006
- Information Disclosure Statements filed on 04/25/2006
- Oath or Declaration filed on 02/09/2006
- Request for Immediate Examination filed on 02/09/2006
- U.S. Basic National Fees filed on 02/09/2006
- Substitute Specification filed on 02/09/2006
- Assignment filed on 04/25/2006
- Priority Documents filed on 02/09/2006
- Power of Attorney filed on 02/09/2006



Low/Base 8-21-06
Matter No 8312-7
Routed to: DMD / Sandy

COPY

The following items **MUST** be furnished within the period set forth below in order to complete the requirements for acceptance under 35 U.S.C. 371:

- Translation of the application into English. Note a processing fee will be required if submitted later than 30 months from the priority date.
- Translation of the application into English. The current translation of the application into English is defective as described below. Note a processing fee will be required if submitted later than 30 months from the priority date.
 - Translation of Original Application as filed has not been submitted.
- Processing fee of \$130 for providing the translation of the application and/or the Annexes later than 30

COPY

months from the priority date (37 CFR 1.492(i)).

SUMMARY OF FEES DUE:

Total additional fees required for this application is \$130 for a Small Entity:

- \$130 for English translation surcharge required.

ALL OF THE ITEMS SET FORTH ABOVE MUST BE SUBMITTED WITHIN TWO (2) MONTHS FROM THE DATE OF THIS NOTICE OR BY 32 MONTHS FROM THE PRIORITY DATE FOR THE APPLICATION, WHICHEVER IS LATER. FAILURE TO PROPERLY RESPOND WILL RESULT IN ABANDONMENT.

The time period set above may be extended by filing a petition and fee for extension of time under the provisions of 37 CFR 1.136(a).

Applicant is reminded that any communications to the United States Patent and Trademark Office must be mailed to the address given in the heading and include the U.S. application no. shown above (37 CFR 1.5)

*A copy of this notice **MUST** be returned with the response.*

BARBARA A CAMPBELL

Telephone: (703) 308-9140 EXT 217

PART 1 - ATTORNEY/APPLICANT COPY

U.S. APPLICATION NUMBER NO.	INTERNATIONAL APPLICATION NO.	ATTY. DOCKET NO.
10/567,794	PCT/EP04/08314	8312-7/05.1816.6.do

FORM PCT/DO/EO/905 (371 Formalities Notice)

COPY

COPY

English Translation of

5

Amended Claims 1 to 17

of April 1, 2005

10

Filed on behalf of

International Preliminary Examination

15

Amended Claims 1 to 17:

1. A process for producing granular activated carbon, in particular spherical activated carbon, by carbonization of suitable carbonaceous polymers in the form of polymer granules, in particular polymer spherules, as a starting material, which polymer granules are convertible by carbonization at least essentially into carbon, wherein the polymer granules, in particular polymer spherules, are continuously moved through a carbonization apparatus comprising a plurality of temperature zones so that an at least essentially complete conversion of the starting material to carbon is effected, wherein the carbonization apparatus comprises at least the following temperature zones in the following order:
- a) optionally, a first temperature zone ("sulfonating zone") where in the case that the starting material contains no groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular no strongly acidic groups such as sulfonic acid groups, or else in the case that such groups are to be additionally introduced into the starting material, these groups are introduced into the starting material, in particular by sulfonation;
 - b) a second temperature zone ("pre-carbonization zone" or "zone of acidic gases"), preferably having a higher average temperature than the first temperature zone, wherein in the second temperature zone the groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular strongly acidic groups such as sulfonic acid groups, are detached or split off from the starting material, so that carbonization and/or thermal decomposition of the starting material ensues, preferably accompanied by crosslinking of the polymers and/or formation of carbon;
 - c) a third temperature zone ("post-carbonization zone"), preferably having a higher average temperature than the second temperature zone, wherein in the third temperature zone further carbonization of the starting material resulting from the second temperature zone is performed, so that an at least essentially complete conversion of the starting material to carbon is effected;
- wherein the individual temperature zones are separately and/or independently controlled.

2. The process according to claim 1, characterized in that the carbonization apparatus used is a belt-oven, in particular an oxidizing belt-oven.
- 5 3. The process according to claim 1 or 2, characterized in that the polymer granules, in particular polymer spherules, are continuously moved through the temperature zones of the carbonization apparatus, in particular of the belt-oven, by means of transporting or conveying means, in particular by means of a moving transporting or conveying belt, such that an at least essentially complete conversion of the starting material to carbon is effected.
- 10 4. The process according to any one of the preceding claims, characterized in that the starting material used comprises polymers in the form of polymer granules, in particular polymer spherules, based on styrene and divinylbenzene and containing chemical groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular strongly acidic groups such as sulfonic acid groups.
- 15 5. The process according to claim 4, characterized in that the chemical groups leading to cross-linkages, in particular strongly acidic groups such as sulfonic acid groups, are already present in the starting material and/or in that the weight ratio of polymers to sulfonic acid groups is in the range from about 5:1 to about 1:1 and in particular in the range from about 2:1 to about 1:1.
- 20 6. The process according to claim 4 or claim 5, characterized in that the starting material used comprises ion-exchanger resins, in particular preferably strongly acidic cation-exchanger resins, in particular ion-exchanger resins having sulfonic acid groups, and/or acidic organic catalysts, such as catalysts for bisphenol synthesis or for MTBE synthesis.
- 25 7. The process according to claim 6, characterized in that the starting material, in particular the ion-exchanger resins and/or the acidic organic catalysts, has added to it before and/or during the carbonization a sulfonating agent, preferably SO_3 , preferably in the form of sulfuric acid and/or oleum, in particular in an amount of about 1 % to about 30 % by weight of SO_3 , in particular 5 % by weight to about 25 % by weight of SO_3 , based on the dry weight of the starting material.
- 30 35 8. The process according to claim 4, characterized in that the chemical groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular strongly acidic groups such as sulfonic acid groups, are, before and/or during the carbonization, introduced into the starting material, in particular by sulfonation, preferably by addition of a sulfonating agent, in particular SO_3 , preferably in the form of oleum and/or sulfuric acid, more preferably in the form of oleum mixed with sulfuric acid, in particular wherein the non-sulfonated polymeric starting material is before being introduced into the carbonization apparatus contacted with the sulfonating agent, preferably such that the polymeric starting material is at least essentially completely wetted with sulfonating agent.
- 40 45

- 5 9. The process according to claim 8, characterized in that the sulfonating agent, in particular concentrated sulfuric acid and/or oleum, is used in relation to the polymeric starting material to be sulfonated in weight-based ratios of sulfonating agent to polymeric starting material in the range from 0.2:1 to 2:1, in particular in the range from 0.4:1 to 1.5:1, and/or in that the weight ratio of polymer to oleum 20 % is up to about 1:1 or more, and/or in that the weight ratio of polymer to oleum 20 % to sulfuric acid is about 1:1:0.5.
- 10 10. The process according to claim 8 or 9, characterized in that the starting material used comprises polymer granules, in particular polymer spherules, based on styrene and divinylbenzene, and/or in that the starting material used comprises precursors of ion-exchanger resins.
- 15 11. The process according to one or more of the preceding claims, characterized in that the polymer granules, in particular polymer spherules, are porous, in particular macroporous, and/or gel-like.
- 20 12. The process according to any one of the preceding claims, characterized in that the individual temperature zones possess separate and/or independent exhaust means, so that the process gases from the different temperature zones are separated and/or separately collected, and/or in that the carbonization apparatus comprises at least one lock, in particular between individual successive temperature zones and/or within individual temperature zones, preferably at least between the second and third temperature zones, so that there is at least essentially no mixing through of process gases from different temperature zones between which at least one lock is disposed, and/or so that the acidic process gases from the second temperature zone are not mixed with the other process gases and can be collected separately, if appropriate followed by disposal or reprocessing with subsequent recycling.
- 25 30 13. The process according to any one of the preceding claims, characterized in that the process control is performed by setting the temperature profile in the individual temperature zones and/or by setting the speed at which the starting material moves through the temperature zones of the carbonization apparatus, and/or in that the total residence time of the starting material in the carbonization apparatus is in the range from 0.1 to 5 hours, in particular in the range from 0.25 to 4 hours and preferably in the range from 0.5 to 3 hours.
- 35 40 14. The process according to any one of the preceding claims, characterized in that the first temperature zone is operated at temperatures in the range of from 50 to 200 °C, in particular in the range of from 75 to 175 °C and preferably in the range of from 100 to 150 °C, and/or in that the second temperature zone is operated at temperatures in the range of from 100 to 500 °C, in particular in the range of from 150 to 450 °C, and/or in that the third temperature zone is operated at temperatures above 400 °C, in particular above 450 °C to 500 °C, and/or in that the third temperature zone is operated at temperatures in the range of from 400 to 1.200
- 45

PCT/EP 2004/008314

°C, in particular in the range of from 450 to 1.000 °C, preferably in the range of from 500 °C to 900 °C and more preferably in the range of from 550 to 850 °C.

- 5 15. The process according to one or more of the preceding claims, characterized in that the carbonized material is subsequently subjected to an activation.
- 10 16. The process according to claim 15, characterized in that the activation is similarly carried out in the carbonization apparatus or else in that the activation is carried out in a distinct apparatus and/or at different locations and/or times than the carbonization.
- 15 17. The process according to claim 15 or 16, characterized in that the activation is carried out in a conventional manner, in particular wherein the activation is carried out in the presence of customary activating gases, such as oxygen, in particular in the form of air, water vapor and/or carbon dioxide or mixtures of these activating gases, preferably in the presence of a mixture of water vapor and nitrogen, and/or in particular wherein the activation is carried out at temperatures in the range of from about 700 to 1.200 °C, in particular in the range of from about 800 °C to about 1.100 °C, preferably in the range of from about 850 °C to about 1.000 °C and more preferably in the range of from about 900 to about 975 °C, and/or in
20 particular wherein the duration of the activation is in the range of from about 0.5 to about 20 hours, in particular in the range of from about 2 hours to about 15 hours and preferably in the range of from about 5 hours to about 10 hours.

PCT/EP 2004/008314

5

English Translation of

Original

10

PCT Filing Text

Activated Charcoal Production

The present invention relates to a process for producing activated carbon, particularly in granule form ("granulocarbon"), preferably in spherical form ("spherocarbon"), and also to the thus produced activated carbon products and their use for various applications, particularly for filters or for protective materials, for example protective suits.

Activated carbon has fairly unspecific adsorptive properties and for this reason is the most widely used adsorbent. Legislative strictures as well as the rising sense of responsibility for the environment lead to a rising demand for activated carbon.

Activated carbon is generally produced by smoldering (also referred to by the synonyms of "carbonization" and "pyrolysis") and subsequent activation of carbonaceous compounds, preferably such starting compounds or reactants that lead to economically reasonable yields because the weight losses through split-off of volatile constituents in the course of smoldering and through burn-out in the course of activation are appreciable. For further details concerning the production of activated carbon, see for example H. v. Kienle and E. Bäder, Aktivkohle und ihre industrielle Anwendung [Activated Carbon and Its Industrial Use], Enke Verlag Stuttgart, 1980.

The constitution of the activated carbon produced – finely or coarsely porous, firm or brittle – is also dependent on the starting material. Examples of customary starting materials are coconut shells, wood wastes, peat, bituminous coal, pitches, but also particular plastics or polymers which play a certain part in the production of woven activated carbon fabrics for example.

Activated carbon is used in various forms: pulverized carbon, splint coal carbon, granulocarbon, molded carbon and also, since the end of the 1970s, spherical activated carbon ("spherocarbon"), as well as fibrous activated carbon ("fibrocarbon", for example in the form of fabrics of activated carbon fibers). Spherical activated carbon in particular has a number of advantages compared with other forms of activated carbon, such as pulverized, splint coal, granulocarbon and the like that make it valuable or even indispensable for certain applications: It is free flowing, enormously abrasion resistant (dustless) and very hard. However, owing to its high cost, its use is essentially limited to protective suits and high-performance filters for noxiants in air-streams.

Granulocarbon, especially spherocarbon, is in great demand on account of its specific shape, but also on account of its extremely high abrasion-resistance, for example for particular fields of use, examples being sheet filters for protective suits against chemical poisons and filters for low noxiant concentrations in large volumes of air. For instance, when reticulated, large-cell polyurethane foams are loaded with activated carbon as described in DE 38 13 563 A1, for example, only a very free-flowing carbon can be used if optimal coverage of the inner layers of the foam material is to be achieved as well. The manufacture of protective suits against chemical poisons on the lines of DE 33 04 349 C3, for example, can likewise utilize only a highly abrasion-resistant carbon, and only spherocarbon fits this description.

Spherocharbon is even now mostly produced by multistage processes which are very costly and inconvenient. The most well-known process consists in spherules being produced from coal tar pitch and suitable asphaltic residues from the petrochemical industry and oxidized (to render them unmeltable), smoldered and activated. For example, spherocarbon can be produced from bitumen in a multistage process. These multistage processes are very cost-intensive and the associated high cost of this spherocarbon prevents many applications wherein spherocarbon ought to be preferable by virtue of its properties.

There have consequently been various attempts to produce high-grade spherocarbon in some other way:

It is prior art to produce spherocarbon by smoldering and subsequent activation of new or used ion-exchangers containing sulfonic acid groups, or by smoldering ion-exchanger precursors in the presence of sulfuric acid and subsequent activation, the sulfonic acid groups and the sulfuric acid respectively having the function of a crosslinker, the yields obtained, which do not depend on whether ready-produced cation-exchanger resins or unsulfonated ion-exchanger precursors are used as starting material, being about 30 % to 50 %, based on organic or polymeric starting material. Such processes are described, for example, in DE 43 28 219 A1 and DE 43 04 026 A1 and also in DE 196 00 237 A1 including the German patent application DE 196 25 069 A1. But these processes are disadvantageous and problematic in particular because of the large amounts of sulfur dioxide released (about 1 kg of SO₂ per kg of end product) and also because of the (partly) associated corrosion problems in the manufacturing equipment. When used ion-exchanger resins, especially used cation-exchanger resins, are used as starting materials, there is also the problem that these, although they have been washed with acid, are contaminated with cations which then accumulate in the end-product, so that the production of major amounts of spherocarbon in consistent quality is consequently very difficult. When ion-exchanger precursors, i.e. polymer spherules without exchanger groups like sulfonic acid groups, are used, it is additionally necessary to use large amounts of sulfuric acid and/or oleum for the crosslinking during the smoldering.

WO 98/07655 A1 describes a process for producing spherules of activated carbon wherein a mixture comprising a distillation residue from diisocyanate production and a carbonaceous processing aid or additive with or without one or more further additives is processed into free-flowing spherules which are subsequently smoldered and then activated. This process likewise releases, in the course of the smoldering step, large pulses of decomposition products, which is associated with the problems described above.

WO 01/83368 A1 describes a process for producing spherical activated carbon by smoldering and activation of polymer spherules based on styrene and divinylbenzene and containing chemical groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, especially sulfonic acid groups, wherein the polymer spherules are initially continuously pre-smoldered and subsequently discontinuously post-smoldered and activated. The two-stage operation of smoldering/carbonization as

PCT/EP 2004/008314

pre-smoldering (i.e. pre-carbonization) and post-smoldering (i.e. post-carbonization) is not always achievable, often as a result of limitation imposed by the equipment actually available.

5 The problem underlying the present invention consists in providing a process for efficient production of activated carbon, particularly in granule or sphere form. The process shall make it possible to produce activated carbon in a less inconvenient and in particular in a very economical manner.

10 Applicant has now found that, surprisingly, the problem underlying the present invention is solved when in the process for producing granular, in particular spherical activated carbon starting from suitable carbonaceous polymers (for example organic polymers) as a starting material which are convertible by carbonization into carbon at least essentially, the step of carbonization is effected by moving the starting material continuously through a carbonization apparatus comprising a plurality of temperature zones
15 (i.e. reaction zones) or a temperature gradient such that an at least essentially complete conversion of the starting material to (elemental) carbon is effected.

The present invention accordingly provides a process according to claim 1.

20 The fundamental principle of the present invention thus consists in conducting the entire carbonization operation, with its various process steps or sectors to be carried out at different temperatures, in just a single apparatus which has to comprise, as proposed, a plurality of temperature zones or a temperature gradient for this purpose. This makes it
25 possible to perform the carbonization operation continuously, i.e., without any interruption, in particular without the apparatus being changed, which allows a not insignificant simplification and efficiency enhancement of the process operation, associated with economic savings.

30 The temperature zones or the temperature gradient on the one hand and, on the other, the speed at which the starting material moves through the carbonization apparatus have to be chosen and in particular conformed to each other such that an at least essentially complete conversion of the carbonizable starting material to carbon is effected. The arrangement and choice of the constitution of the temperature zones or of the temperature
35 gradient in cooperation with the speed at which the starting material moves through the carbonization apparatus constitute means for specifically controlling or influencing the processing sequence of the present invention.

In general, the conveying of the starting material according to the present invention is effected in that the starting material is continuously moved through the temperature
40 zones and/or the temperature gradient of the carbonization apparatus by means of transporting or conveying means, in particular by means of a moving transporting or conveying belt, such that an at least essentially complete conversion of the starting material to carbon is effected. The speed of the conveying belt has to be conformed to the temperature profile of the temperature zones or of the temperature gradient, and/or vice versa.

45

PCT/EP 2004/008314

The carbonization apparatus used for carrying out the process of the present invention is for example a continuous rotary tube or a continuous rotary tube oven; here, the charged material, i.e., the carbonizable starting material, can be conveyed or transported by means of suitable transporting or conveying means, respectively, through the rotary tube or through the rotary tube oven, examples being suitable propulsive bodies, for example a screw conveyor. It is similarly possible to transport or convey the charged material through appropriate inclination of the rotary tube or the rotary tube oven. It is similarly possible to provide a combination of the aforementioned measures to transport or convey the charged material through the rotary tube or through the rotary tube oven.

A so-called belt-oven, in particular a so-called oxidizing belt-oven (i.e. oxidation belt-oven), is a particularly suitable carbonization apparatus for carrying out the process of the present invention. Such systems are marketed by numerous firms, for example by Sarnes Ingenieure of Ostfildern in Germany, and comprise in general a combined unit of transporting/conveying belt on the one hand and oven/heating apparatus on the other, the material to be treated in the oven or heating means being transportable or conveyable through the interior of the oven or heating means via the transporting/conveying belt.

Useful starting materials for the inventive production of activated carbon are smolderable or carbonizable polymers, i.e. carbonaceous polymers convertible by pyrolysis or carbonization to elemental carbon at least essentially.

The form or shape of the polymeric starting material is in general at least essentially or substantially preserved in the carbonization operation, which with or without subsequent activation does however give rise to a reduction in the particle size or particle diameter. Consequently, to produce activated carbon in granule form, in particular in sphere form, polymer granules or spherules, i.e. polymers in granule or sphere form or substantially in granule or sphere form, have to be used as starting materials (the polymer granules or spherules used according to the present invention generally have diameters of up to about 2 mm and in particular of up to about 1.5 mm or less). Similarly, the particle size of the granulo- or spherocarbon obtained depends on the size of the granules or spherules in the starting material. Commercially available starting materials generally lead to activated carbon granules or spherules about 0.1 mm to about 2.0 mm in diameter, in particular in the range from about 0.2 mm to about 1.0 mm and preferably in the range from about 0.3 mm to about 0.8 mm, with average values in the range from about 0.4 mm to about 0.6 mm.

The polymeric starting material may be for example in porous, in particular macroporous, and/or gel-like form. In the case of gel-like starting materials, preference is given to using microporous polymeric particles. Preference is given to using macroporous or microporous gel-like starting materials. Because the form or shape of the polymeric starting material is in general at least essentially or substantially preserved in the carbonization operation, the properties, in particular the morphology (for example porosity), of the smoldered/carbonized products can be controlled or influenced through spe-

cific choice of the starting material. For example, the porosity of the starting material also determines the porosity of the smoldered/carbonized products.

5 Useful starting materials include for example organic polymeric granules or spherules which possess a polymeric skeleton consisting essentially of polystyrene, in which case the polystyrene chains can be locally connected or crosslinked by means of a component having at least two vinyl groups per molecule, in particular divinylbenzene, and the polymer skeleton may contain functional chemical groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular sulfonic acid groups. More particularly, the starting material used for the inventive production of granular or spherical activated carbon comprises organic polymeric granules or spherules based on divinylbenzene-crosslinked polystyrene which contain functional chemical groups, in particular acidic groups such as sulfonic acid groups, which, when thermally decomposed, lead to free radicals and thus to cross-linkages; the divinylbenzene content may be up to about 20 % by weight, in particular up to about 15 % by weight and preferably up to about 10 % by weight, based on the polymer spherules. But instead of divinylbenzene, the polystyrene may also be crosslinked using a comparable organic, in particular aromatic organic compound having at least two crosslinking groups, in particular vinyl groups, per molecule that is suitable for crosslinking polystyrene.

20 The weight ratio of polymer to chemical groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular the weight ratio of polymer to sulfonic acid groups, can vary within wide limits; advantageously, it is generally in the range of from about 5:1 to about 1:1, in particular in the range of from about 2:1 to about 1:1. It is nonetheless possible to depart from the values mentioned.

25 In a first embodiment of the process according to the present invention, the chemical groups leading to cross-linkages, in particular strongly acidic groups such as sulfonic acid groups, are already present in the starting material.

30 Nonlimiting examples of polymeric starting materials where the chemical functional groups, in particular sulfonic acid groups, leading to cross-linkages in the course of carbonization or pyrolysis are already present in the actual starting material are ion-exchanger resins, in particular strongly acidic cation exchanger resins, such as cation-exchanger resins, having sulfonic acid groups. The ion-exchanger resins in question may be unused ion-exchanger resins or else used ion-exchanger resins. In the case of used cation-exchangers, these may be contaminated with metal ions which are then present in the end-product as catalytic metallic impregnation. In the case that used or spent ion-exchangers are used as starting material, the present invention similarly concerns a process for disposing of used or spent ion-exchangers. This is because the process of the present invention is able to convert the used ion-exchangers to be disposed of into a useful product – i.e. activated carbon – which contributes to environmental protection by virtue of its ability to adsorb environmental poisons.

45

A further example of polymeric starting materials wherein the chemical functional groups, in particular sulfonic acid groups, leading to cross-linkages in carbonization or pyrolysis are already present in the actual starting material is acidic organic catalysts, for example catalysts for bisphenol synthesis or for MTBE (methyl tert.-butyl ether) synthesis, preferably organic catalysts containing sulfonic acid groups. Particular preference is given to acidic organic catalysts of the above-described kind which may be porous and/or gel-like. This is because applicant has surprisingly found that for example the deactivated acidic organic catalysts generated in MTBE or bisphenol synthesis are a good starting material for the production of granulo- or spherocarbon. The granular or spherical catalyst material coming from the bisphenol or MTBE synthesis reactor – if appropriate after washing and drying – can then be smoldered/carbonized and, if appropriate, activated according to the present invention. Still-adhering phenol in the case of catalysts from the bisphenol process is destroyed in the carbonization or pyrolysis or/and burned in the post-carbonization step. The yields of activated carbon granules or spherules in the case of the organic catalysts are similar to those obtained in the case of cation exchangers. Unlike with used ion exchangers, however, with used organic catalysts there is no need to consider the problem of cations accumulating in the carbon. According to the present invention, the spent or exhausted acidic organic catalysts from MTBE synthesis or from the synthesis of bisphenol from phenol and acetone which are generated as waste can readily be used as starting materials and disposed of in this way. When spent or deactivated acidic polymeric organic catalysts based on styrene and divinylbenzene, in particular from the MTBE process or from the bisphenol process, are used as starting material, the present invention similarly concerns a process for disposing of spent catalysts or catalysts which have become inert. The process of the present invention makes it possible to convert the wastes to be disposed of into a useful product – activated carbon – which contributes to environmental protection by virtue of its ability to adsorb environmental poisons.

Even though the chemical groups, in particular strongly acidic groups such as sulfonic acid groups, leading to cross-linkages are already present in the starting material, it may be preferable to contact the starting material, in particular the ion-exchanger resins or the acidic organic catalysts, before and/or during the carbonization with a sulfonating agent, preferably SO_3 , more preferably in the form of sulfuric acid and/or oleum, in particular in an amount from about 1 % to about 30 % by weight of SO_3 and in particular 5 % by weight to about 25 % by weight of SO_3 , based on the dry weight of the starting material; this additionally increases the number of free radicals formed in the carbonization and leads to increased cross-linkages in the polymers, so that finally more stable or more compact, in particular more abrasion-resistant, end-products in the form of carbon granules or carbon spherules result and more particularly the yield of activated carbon is increased as well. As well as increasing the yield of end product or activated carbon, the times for the carbonization can also be distinctly shortened as a result. This is because, as applicant has found, the yields of activated carbon can be increased with increasing acid content or sulfonic acid group content of the starting material. For example, starting materials, in particular ion-exchangers or catalysts, having a lower acid content can be admixed with some oleum and/or sulfuric acid to improve the yield. Normally, for example, about 1 % to about 30 % by weight of bound or free SO_3 , based

on the polymer fraction in the starting material, is sufficient. The introduction of additional sulfonic acid groups by sulfonation can be carried out either as a separate process step outside the carbonization apparatus (either continuously or discontinuously) or else advantageously in the carbonization apparatus itself, as more particularly described
5 hereinbelow. This offers the decisive advantage that not just the entire carbonization operation can be carried out continuously within one apparatus, but the additional sulfonation too can take place in the same apparatus as a process step upstream of the carbonization operation.

10 In a further, alternative embodiment of the process according to the present invention, the chemical groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular strongly acidic groups such as sulfonic acid groups, are introduced into the starting material before and/or during the carbonization operation. This can be done for example by sulfonating the polymeric starting material, preferably
15 by addition of a sulfonating agent, in particular SO_3 , preferably in the form of oleum and/or sulfuric acid, more preferably in the form of oleum mixed with sulfuric acid. The unsulfonated starting material is contacted with the aforementioned sulfonating agent, for example by mixing the polymer granules or spherules with the sulfonating agent, in particular oleum and/or sulfuric acid, for which care should be taken to ensure that the
20 polymeric starting material is contacted or mixed very homogeneously and completely with the sulfonating agent without "dry places/zones" (i.e. unwetted places/zones of the starting material) being left behind on the starting material. This can be ensured by using an excess of sulfonating agent to produce a "wet mix" in the form of a homogeneous porridge which then, under elevated temperatures, finally leads to the sulfonation of
25 the starting material. But it is particularly preferable for the non-sulfonated polymeric starting material (in particular a starting material in the form of polymer granules or spherules, preferably based on divinylbenzene-crosslinked polystyrene) to be contacted, before introduction to the carbonization apparatus, with the sulfonating agent such that an at least essentially complete wetting of the polymeric starting material or of the
30 polymer granules or spherules with the sulfonating agent is ensured; this is advantageously accomplished by contacting the non-sulfonated polymeric starting material with the sulfonating agent in suitable mixing means by intensive mixing or commixing, preferably such that an at least essentially complete wetting of the polymeric starting material takes place, preferably in a twin-screw extruder to which the polymeric starting
35 material to be sulfonated and the sulfonating agent can be fed in a suitable manner (for example via separate feed channels); this particular embodiment has the advantage that a homogeneous, uniform and essentially complete wetting of the polymeric starting material with the sulfonating agent is achieved and, on the other hand, favorable mixing ratios, in particular relatively low amounts of sulfonating agent, can be used by virtue of
40 the intensive co-mixing; in other words, a (large) excess of sulfonating agent does not have to be used; the aforementioned particular embodiment, which utilizes mixing means ensuring intensive co-mixing of the sulfonating agent with the polymeric starting material to be sulfonated, further provides relatively short residence times, which is favorable with regard to the process sequence, since high throughputs can be achieved.
45 Preferably, the contacting of the non-sulfonated polymeric starting material with the sulfonating agent takes place in a temperature range between room temperature (about

20 °C) and at temperatures below the melting point or melting range of the polymeric starting material, preferably in the range from about 20 °C to about 100 to 150 °C, preferably at room temperature. Useful sulfonating agents include in particular sulfuric acid, oleum and sulfuric acid/oleum mixtures; the sulfuric acid used is preferably concentrated sulfuric acid, more preferably 90 % to 100 % sulfuric acid, even more preferably in a mixture with oleum (oleum is a particular form of concentrated sulfuric acid which contains varying amounts of sulfur trioxide SO_3 ; 20 % oleum for example contains 20 % of sulfur trioxide). In general, the sulfonating agent (in particular concentrated sulfuric acid and/or oleum) is used in relation to the polymeric starting material to be sulfonated in weight-based ratios of sulfonating agent to polymeric starting material in the range from 0.2:1 to 2:1, in particular in the range from 0.4:1 to 1.5:1.

The unsulfonated starting material is suitably sulfonated using in particular oleum, in which case the polymer/oleum 20 % weight ratio can be up to about 1:1 or more for example, or else oleum-sulfuric acid mixtures, in which case the polymer/oleum 20 %/sulfuric acid weight ratio can be about 1:1:0.5 for example.

The sulfonation itself can be carried out as a separate process step outside the carbonization apparatus (either continuously or discontinuously) or else advantageously in the carbonization apparatus itself, as will be more particularly described hereinbelow. The last-mentioned possibility offers the decisive advantage that not just the entire carbonization operation can be carried out within one apparatus and continuously but also – in the case of unsulfonated starting materials or starting materials having low sulfonic acid group contents – the sulfonation can be provided in the same apparatus as a process step upstream of the carbonization operation.

This second embodiment, which utilizes starting materials where the chemical groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages (for example strongly acidic groups such as sulfonic acid groups) have to be introduced into the starting material before and/or during carbonization, offers the advantage over the first embodiment that less costly materials are used.

Examples of starting materials suitable according to the present invention which are in accordance with the second embodiment and where chemical groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages (examples being strongly acidic groups such as sulfonic acid groups) are introduced into the starting material before and/or during the carbonization operation are for example polymer granules, in particular polymer spherules, based on styrene and divinylbenzene, for example precursors of ion-exchanger resins, as described above. The precursors for ion-exchangers can in principle be gel-like or macroporous. The latter are significantly more expensive, mainly on account of their considerably higher divinylbenzene content. Their numerous mesopores are fully preserved during the conversion into activated carbon, and this is important for some applications. The gel-types, by contrast, lead to markedly microporous carbons. The pore volume may be up to 90 % to 95 % present as micropores. The gel-types often contain about 2 % to about 8 % of divinylbenzene. But even only lightly crosslinked types having a lower level of divinylbenzene (about 2 %

PCT/EP 2004/008314

to 4 % of divinylbenzene) survive the severe swelling in the acid, thus do not burst or break apart into semispheres. It has emerged that types having a very low divinylbenzene content are very suitable for the purposes of the present invention. A much more important aspect is the sulfonation, which has to be as complete as possible, since the decomposition of the sulfonic acid groups gives rise to those free radicals which lead to the cross-linkages responsible for the yield. While not only macroporous but also gel-types can be used when starting from cation-exchangers and the choice is more a question of economics, gel-types are preferred when precursors of ion-exchangers (= pure polymers) are used. The reason is as follows: The macroporous precursors absorb a great deal of acid or oleum in their large pores in the manner of a sheet of blotting paper, so that the mixture of polymer and acid is dry or sandy and a uniform distribution of the acid is scarcely achieved. Apart from that, however, the carbonization and activation of cation-exchangers leads to comparable products than when starting from precursors and acid.

To carry out the process of the present invention, a preferred embodiment of the present invention is characterized in that the carbonization apparatus comprises at least the following temperature zones in the following order:

- a) optionally, a first temperature zone ("sulfonating zone") where in the case that the starting material contains no groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular no strongly acidic groups such as sulfonic acid groups, or else in the case that such groups are to be additionally introduced into the starting material, these groups are introduced into the starting material, in particular by sulfonation;
- b) a second temperature zone ("pre-carbonization zone" or "zone of acidic gases"), preferably having a higher average temperature than the first temperature zone, wherein in the second temperature zone the groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular strongly acidic groups such as sulfonic acid groups, are detached or split off from the starting material, so that carbonization and/or thermal decomposition of the starting material ensues, preferably accompanied by a crosslinking of the polymers and/or a formation of carbon; and
- c) at least one third temperature zone ("post-carbonization zone"), preferably having a higher average temperature than the second temperature zone, wherein in the third temperature zone further carbonization of the starting material resulting from the second temperature zone is performed, so that an at least essentially complete conversion of the starting material to carbon is effected.

The process of the present invention thus offers the decisive advantage that the entire smoldering or carbonizing operation, i.e. pre-carbonization plus post-carbonization, and additionally, if appropriate, the preceding sulfonating operation, can be operated continuously in a single apparatus.

As stated above, a first temperature zone a) can for the case that the starting material contains no groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular no strongly acidic groups such as sulfonic acid groups, or else for the case that such groups are to be additionally introduced into the starting material, can be the location for the introduction or the additional introduction of these groups into the starting material, in particular by sulfonating. This is why this zone is also referred to as "sulfonating zone". Sulfonating is effected in a conventional manner as already described. In general, the first temperature zone is operated for this purpose at temperatures in the range of from 50 to 200 °C, in particular in the range from 75 to 175 °C and preferably in the range from 100 to 150 °C. However, this temperature zone is optional and can be dispensed with if, for example, starting material having a sufficient content of groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular sulfonated starting material (for example strongly acidic cation-exchangers having sulfonic acid groups), is used or else the sulfonation is carried out separately in an upstream step. Advantageously, when an unsulfonated polymeric starting material is used, this starting material is contacted with the sulfonating agent before introduction into the sulfonating zone, preferably such that an at least essentially complete wetting of the polymeric starting material or of the polymer granules or spherules with the sulfonating agent is ensured; for further details in this regard, see the above observations.

The two subsequent temperature zones b) and c) then effect the carbonization of the sulfonated starting material, i.e. in two stages, namely pre-carbonization b) (second temperature zone or "pre-carbonization zone") and post-carbonization c) (third temperature zone or "post-carbonization zone"). Since the pre-carbonization b) in the second temperature zone releases, through the specific decomposition of the starting material, acidic gases (mainly SO₂, as well as small amounts of SO₃, H₂SO₄ and also, if appropriate, other acidic gases), this zone is also referred to as "zone of acidic gases". The third temperature zone or post-carbonization zone c), by contrast, does not release any acidic gases, but predominantly carbon oxides, such as carbon monoxide and carbon dioxide, hydrocarbons, hydrogen and water.

The temperatures at which the second and third temperature zones b) and c) can be operated can vary within wide limits. For example, the second temperature zone b) can be operated at temperatures in the range from 100 to 500 °C and in particular in the range from 150 to 450 °C. The third temperature zone c) can be operated for example at temperatures above 400 °C, in particular above 450 °C to 500 °C, for example at temperatures in the range from 400 to 1.200 °C, in particular in the range from 450 to 1.000 °C, preferably in the range from 500 °C to 900 °C and more preferably in the range from 550 to 850 °C.

Smoldering – also referred to by the synonyms of "carbonization" or "pyrolysis" and consisting in the case of the present invention of pre-carbonization b) (second temperature zone) and post-carbonization (third temperature zone) – converts the carbonaceous starting material to carbon; in other words, the starting material is carbonized or carbonized. Smoldering or carbonization, which detaches or sets free volatile constituents such

PCT/EP 2004/008314

as in particular SO_2 , destroys the functional chemical groups, in particular sulfonic acid groups, to form free radicals which effect the pronounced crosslinking without which there would be no pyrolysis residue (= carbon). In general, the pyrolysis or carbonization is carried out under an inert atmosphere (for example nitrogen) or an at most
5 slightly oxidizing atmosphere. It can similarly be advantageous for the inert atmosphere of the carbonization operation, in particular if it is carried out at comparatively high temperatures (for example in the range from about 500 °C to 650 °C), to be admixed with a minor amount of oxygen, especially in the form of air (for example 1 % to 5 %) in order that an oxidation of the carbonized polymer skeleton may be effected and activation may thereby be facilitated.
10

Advantageously, the individual temperature zones are separately or independently controllable. The individual temperature zones can each be assigned takeoff means, in which case it may be preferable for the individual temperature zones to be assigned
15 separate or independent takeoff means, so that the process gases from the different temperature zones can be separated or separately collected (an example being the separate collection of the acidic process gases). This makes it possible for example to separate the acidic or corrosive phase (pre-carbonization, associated with SO_2 emission) from the high-temperature phase (post-carbonization). This is because applicant has found
20 that pre-smoldered/pre-carbonized starting material does not release any acidic or corrosive entities as the temperature is further increased.

It may similarly be preferable to provide the carbonization apparatus with at least one lock (i.e. a sluice or transfer canal), in particular between individual successive temperature zones and/or within individual temperature zones, preferably at least between
25 the second and third temperature zones, so that there is at least essentially no mixing through of process gases from different temperature zones between which at least one lock is disposed; this makes it possible to ensure that the acidic process gases (in particular SO_2) from the second temperature zone are not mixed with the other process
30 gases for example and can be collected separately, if appropriate followed by disposal or reprocessing with subsequent recycling. For instance, the SO_2 continuously expelled during the pre-carbonization in particular can be regenerated, in particular via a catalytic oxidation to SO_3 and further conversion to sulfuric acid and/or oleum. The presence of one or more locks similarly makes it possible for gas to be specifically added to
35 individual temperature zones (examples being the addition of minor amounts of oxygen) or to maintain a certain gas composition in certain temperature or reaction zones or parts of temperature or reaction zones (for example an inert atmosphere in parts of the pre-carbonization zone and a slightly oxidizing atmosphere in parts of the post-carbonization zone).
40

For advantageous process management, it is advisable to provide continuous temperature transitions between the individual temperature zones and also within any one individual temperature zone and avoid large temperature differences (i.e. "temperature jumps"). This makes it possible to obtain particularly high-quality products, since in
45 particular bursting or shattering of the starting materials, as can occur when temperature jumps are large, is avoided. It is therefore similarly advisable for advantageous process

PCT/EP 2004/008314

management to provide a temperature gradient within any one individual temperature or reaction zone as well, preferably such that the transition to the next temperature or reaction zone is at least essentially continuous, i.e. not abrupt.

- 5 The process control can be specifically controlled by setting the temperature profile in the individual temperature zones and/or the temperature profile of the temperature gradient and/or by setting the speed at which the starting material moves through the temperature zones and/or the temperature gradient of the carbonization apparatus.
- 10 The total residence time of the starting material in the carbonization apparatus is not critical and can vary within wide limits. It is generally in the range from 0.1 to 5 hours, in particular in the range from 0.25 to 4 hours and preferably in the range from 0.5 to 3 hours.
- 15 Carbonization is generally followed by an activation of the smoldered/carbonized material. This activation is generally effected under conditions known per se. The basic principle of activation is for a portion of the carbon generated in the course of carbonization to be selectively and specifically degraded under suitable conditions. This gives rise to numerous pores, fissures and cracks and the surface area of a unit mass increases appreciably. Activation thus amounts to a specific burn-out of the carbon. Since carbon is degraded in the course of the activation, this operation is accompanied by a loss of substance which may be appreciable and which under optimal conditions is equivalent to an increase in the porosity and an increase in the internal surface area (pore volume). Activation is therefore effected under selective or controlled, oxidizing conditions. Customary activating gases are generally oxygen, in particular in the form of air, water vapor and/or carbon dioxide and also mixtures of these activating gases. Since there is a danger with oxygen that it will act not selectively but over the entire surface (as a result of which the carbon burns off to a greater or lesser extent), water vapor and carbon dioxide are preferred. Very particular preference is given to water vapor, if appropriate mixed with an inert gas (nitrogen for example). To achieve an industrially adequate reaction rate, the activation is generally carried out at temperatures in the range from about 700 °C to about 1.200 °C, in particular in the range from about 800 °C to about 1.110 °C, preferably in the range from about 850 °C to about 1.000 °C and more preferably in the range from about 900 °C to about 975 °C. The duration of the activation can vary within wide limits and can for example be in the range from about 0.5 to about 6 hours, in particular in the range from about 1.5 to about 5 hours and preferably in the range from about 2 to about 3.5 hours.
- 35 According to the invention, the activation can be carried out in particular with a mixture of water vapor and nitrogen, in particular at temperatures in the range from about 850 °C to about 960 °C and preferably in the range from about 910 °C to about 930 °C. The residence times can range from about 0.5 to about 20 hours, in particular from about 2 hours to about 15 hours and preferably from about 5 hours to about 10 hours.
- 40

The activation can in principle also be carried out in the carbonization apparatus. But in general the activation is carried out in a distinct apparatus, in particular at separate locations and times than the carbonization.

5 The sole figure shows a diagram of a typical sequence for the inventive process according to a particular embodiment. The smolderable or carbonizable starting material 4a, for example polymer spherules based on divinylbenzene-crosslinked polystyrene, i.e. unsulfonated starting material, is provided in 1. The unsulfonated starting material 4a is then contacted with a suitable sulfonating agent, in particular sulfur trioxide, preferably
10 in the form of an oleum-sulfuric acid mixture, and subsequently introduced portion-wise into dedicated reaction vessels 5 which continuously move on a suitable transporting or conveying means, in particular a moving transporting or conveyor belt, through the carbonization apparatus 2, in particular a belt oven, in the direction r. The carbonization apparatus comprises in the case of the illustrated embodiment three temperature
15 zones which are each separated from each other by locks 7a, 7b, so that at least essentially no co-mixing of process gases from different temperature zones between which a lock 7a, 7b is disposed can take place, more particularly the acidic process gases from the second temperature zone are not commixed with the other process gases and can be collected separately. The starting material 4b contacted with the sulfonating agent is initially sulfonated in the first temperature zone of the carbonization apparatus 2 and subsequently introduced into a second temperature zone for pre-carbonization, in the
20 course of which the sulfonic acid groups are detached or split off from the starting material, so that carbonization ensues with crosslinking of the free radicals formed. Finally, the thus pre-carbonized material 4c is transported via the transporting or conveying means 6 into a third temperature zone where it is finally further carbonized to form the carbonized product 4d. This can subsequently be fed to an activation 3 to obtain carbonized and activated carbon in sphere form.

The present invention further provides the products produced or producible by the process of the present invention, i.e. activated carbon in granule or sphere form. The continuous operation of the process wherein the starting polymers are continuously, i.e. uninterrupted, in particular without cooling of the pre-carbonized intermediate products, subjected to carbonization, gives activated carbon having improved properties, in particular having improved mechanical and adsorptive properties. This is because applicant
35 has found that a discontinuous operation in the case of carbonization with separation between pre-carbonization and post-carbonization, as customary in the prior art, in particular with isolation of the pre-carbonized products with intervening cooling, is deleterious with regard to the end-products. But this is precisely what is avoided by the process of the present invention.

40 As mentioned above, the particle size of the granulo- or spherocarbon obtained depends on the starting material. Commercially available starting materials generally lead to activated carbon granules or spherules having diameters of up to about 2 mm, in particular of up to about 1.5 mm or less, for example in the range from about 0.1 mm to about
45 1.0 mm, in particular in the range from about 0.2 mm to about 0.8 mm in diameter, having average values in the range from about 0.4 mm to about 0.5 mm. The spherical form

PCT/EP 2004/008314

5 of the starting materials is preserved during carbonization and activation. In other words, the form of the starting materials makes it possible to control and determine the particle size of the end-product in a specific manner, and this constitutes a further advantage of the process according to the present invention. The diameter of the thus produced activated carbon granules or spherules is about 0.1 mm less than that of the starting polymers, so that the diameter of the spherocarbon can be controlled through appropriate selection of the starting material. Sphere diameters in the range from about 0.2 mm to about 1.0 mm, in particular in the range from about 0.3 mm to about 0.8 mm, with averages in the range from about 0.4 mm to about 0.6 mm, are particularly useful for most applications.

15 The activation makes it possible to obtain internal surface areas in the range from about 800 m²/g to about 1500 m²/g and preferably in the range from about 900 m²/g to about 1200 m²/g. The bursting pressure of an individual activated carbon granule or spherule is generally in the range from about 5 Newtons to about 20 Newtons. The bulk weight (apparent density) is in the range from about 400 g/l to about 800 g/l and preferably in the range from about 500 g/l to about 750 g/l.

20 The granulo- or spherocarbon obtained according to the present invention is very abrasion-resistant, free-flowing, dustless and very pressure-resistant. The present invention similarly provides activated carbon granules or spherules of high strength, in particular abrasion-resistant strength, producible by the process of the present invention.

PCT/EP 2004/008314

5 The activity of the spherocarbon is importantly determined by the pores in the activated carbon, in particular by the micropores having a diameter of up to about 20 Å, since most of the molecules to be absorbed are on this order of magnitude. The micropores are generally also responsible for the main fraction of the internal surface area of the ac-
10 tivated carbon. In addition, the so-called mesopores – occasionally also referred to as transitional or conducting pores – having diameters in the range from about 20 to about 500 Å are of importance. In addition, there is also a fraction of still larger macropores. The properties of the end products can be controlled in a specific manner through the choice of starting materials and the process management for the activating step. A high
15 fraction of micropores is desirable.

One skilled in the art will know that pore volume, pore diameter and pore distribution vary according to the degree of activation and the pore system and the pore structure, in particular the pore diameter, and also the surface structure of the end product can be in-
20 fluenced in a specific manner through temperature and activation, so that reference may be made to the pertinent technical literature in this regard.

The activated carbon granules or spherules produced by the process of the present in-
25 vention exhibit good to excellent adsorptive properties. It is further possible to influ-
20 ence or modify the adsorptive properties of the activated carbon granules or spherules produced according to the present invention by impregnation with catalysts (enzymes, metals such as for example copper, silver, platinum, chromium, zinc, mercury, palla-
dium, cadmium, iron, etc. and also compounds of these metals). The activated carbon product obtained according to the production process of the present invention may thus
25 comprise a catalytically effective component, preferably a compound of a catalytically active metal. The impregnation of activated carbon with catalysts is perfectly familiar to one skilled in the art, so that reference may be made to the pertinent technical literature in this regard.

30 The activated carbon granules or spherules produced by the process of the present in-
vention can be used for a very wide variety of applications. The activated carbon gran-
ules or spherules produced by the process of the present invention can find utility for
example for producing adsorption materials such as adsorption (sheet) filters, filter
35 mats, odor filters, sheet filters for protective suits, in particular for the civilian and/or
military sector, filters for indoor air cleaning, gas mask filters and adsorption-capable
supporting structures or else for protective materials, in particular protective suits
against chemical poisons such as warfare agents, or for filters, in particular filters for
removing noxious, poisonous and/or odoriferous entities from air or gas streams.

40 The present invention thus also provides adsorption materials, in particular filters of any
kind such as adsorption (sheet) filters, filter mats, odor filters, sheet filters for protective
suits, in particular for the civilian and/or military sector, such as protective suits against
chemical poisons such as warfare agents, filters for indoor air cleaning, and also protec-
45 tive suits, gas mask filters, filters for removing noxious, poisonous and/or odiferous en-
tities from air or gas streams produced therefrom and adsorption-capable supporting

PCT/EP 2004/008314

structures comprising activated carbon granules or spherules produced according to the present invention.

- 5 Numerous further refinements, variations or modifications of the present invention will appear conceivable to one skilled in the art who reads the description without his or her leaving the realm of the present invention.

PCT/EP 2004/008314

Claims:

1. A process for producing granular, particularly spherical activated carbon by carbonization of suitable carbonaceous polymers in the form of polymer granules, in particular polymer spherules, as a starting material, which are convertible by carbonization into carbon at least essentially,
5
characterized in
10 that the polymer granules, in particular the polymer spherules, are continuously moved through a carbonization apparatus comprising a plurality of temperature zones and/or a temperature gradient so that an at least essentially complete conversion of the starting material to carbon is effected.
- 15 2. The process according to claim 1, characterized in that the carbonization apparatus used is a continuous rotary tube or a continuous rotary tube oven, or else in that the carbonization apparatus used is a belt oven, in particular an oxidizing belt oven.
- 20 3. The process according to claim 1 or 2, characterized in that the polymer granules, in particular polymer spherules, are continuously moved through the temperature zones and/or the temperature gradient of the carbonization apparatus, in particular of the belt oven, by means of transporting or conveying means, in particular by means of a moving transporting or conveying belt, such that an at least essentially
25 complete conversion of the starting material to carbon is effected.
- 30 4. The process according to any one of the preceding claims, characterized in that the starting material used comprises polymers in the form of polymer granules, in particular polymer spherules, based on styrene and divinylbenzene and containing chemical groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular strongly acidic groups such as sulfonic acid groups.

PCT/EP 2004/008314

5. The process according to claim 4, characterized in that the chemical groups leading to cross-linkages, in particular strongly acidic groups such as sulfonic acid groups, are already present in the starting material and/or in that the weight ratio of polymers to sulfonic acid groups is in the range from about 5:1 to about 1:1 and in particular in the range from about 2:1 to about 1:1.
5
6. The process according to claim 4 or claim 5, characterized in that the starting material used comprises ion-exchanger resins, in particular preferably strongly acidic cation exchanger resins, in particular ion-exchanger resins having sulfonic acid groups, and/or acidic organic catalysts, such as catalysts for bisphenol synthesis or for MTBE synthesis.
10
7. The process according to claim 6, characterized in that the starting material, in particular the ion-exchanger resins and/or the acidic organic catalysts, has added to it before and/or during the carbonization a sulfonating agent, preferably SO_3 , preferably in the form of sulfuric acid and/or oleum, in particular in an amount of about 1 % to about 30 % by weight of SO_3 , in particular 5 % by weight to about 25 % by weight of SO_3 , based on the dry weight of the starting material.
15
8. The process according to claim 4, characterized in that the chemical groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular strongly acidic groups such as sulfonic acid groups, are, before and/or during the carbonization, introduced into the starting material, in particular by sulfonation, preferably by addition of a sulfonating agent, in particular SO_3 , preferably in the form of oleum and/or sulfuric acid, more preferably in the form of oleum mixed with sulfuric acid, in particular wherein the non-sulfonated polymeric starting material is before being introduced into the carbonization apparatus contacted with the sulfonating agent, preferably such that the polymeric starting material is at least essentially completely wetted with sulfonating agent.
20
25
30

PCT/EP 2004/008314

- 5 9. The process according to claim 8, characterized in that the sulfonating agent, in particular concentrated sulfuric acid and/or oleum, is used in relation to the polymeric starting material to be sulfonated in weight-based ratios of sulfonating agent/polymeric starting material in the range of from 0.2:1 to 2:1, in particular in the range of from 0.4:1 to 1.5:1, and/or in that the weight ratio of polymer/oleum 20 % is up to about 1:1 or more, and/or in that the weight ratio of polymer/oleum 20 %/sulfuric acid is about 1:1:0.5.
- 10 10. The process according to claim 8 or 9, characterized in that the starting material used comprises polymer granules, in particular polymer spherules, based on styrene and divinylbenzene, and/or in that the starting material used comprises precursors of ion exchanger resins.
- 15 11. The process according to one or more of the preceding claims, characterized in that the polymer granules, in particular polymer spherules, are porous, in particular macroporous, and/or gel-like.
- 20 12. The process according to any one of the preceding claims, characterized in that the carbonization apparatus comprises at least the following temperature zones in the following order:
- 25 a) optionally, a first temperature zone ("sulfonating zone") where in the case that the starting material contains no groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular no strongly acidic groups such as sulfonic acid groups, or else in the case that such groups are to be additionally introduced into the starting material, these groups are introduced into the starting material, in particular by sulfonation; then
- 30 b) a second temperature zone ("pre-carbonization zone" or "zone of acidic gases"), preferably having a higher average temperature than the first temperature zone, wherein in the second temperature zone the groups which, when thermally decomposed, lead to free radicals and thus to cross-linkages, in particular strongly acidic groups such as sulfonic acid groups, are detached of split off from the starting material, so that carbonization and/or thermal decomposition of the starting material ensues, preferably accompanied by a crosslinking of the polymers and/or a formation of carbon; and then
- 35 c) a third temperature zone ("post-carbonization zone"), preferably having a higher average temperature than the second temperature zone, wherein in the third temperature zone further carbonization of the starting material resulting from the second temperature zone is performed, so that an at least essentially complete conversion of the starting material to carbon is effected.
- 40
- 45 13. The process according to any one of the preceding claims, characterized in that the individual temperature zones are separately and/or independently controllable, and/or in that the individual temperature zones possess separate and/or independ-

PCT/EP 2004/008314

- ent exhaust means, so that the process gases from the different temperature zones are separated and/or separately collected, and/or in that the carbonization apparatus comprises at least one lock, in particular between individual successive temperature zones and/or within individual temperature zones, preferably at least between the second and third temperature zones, so that there is at least essentially no mixing through of process gases from different temperature zones between which at least one lock is disposed, and/or so that the acidic process gases from the second temperature zone are not mixed with the other process gases and can be collected separately, if appropriate followed by disposal or reprocessing with subsequent recycling.
14. The process according to any one of the preceding claims, characterized in that the process control is performed by setting the temperature profile in the individual temperature zones and/or the temperature profile of the temperature gradient and/or by setting the speed at which the starting material moves through the temperature zones and/or the temperature gradient of the carbonization apparatus, and/or in that the total residence time of the starting material in the carbonization apparatus is in the range from 0.1 to 5 hours, in particular in the range from 0.25 to 4 hours and preferably in the range from 0.5 to 3 hours.
15. The process according to any one of the preceding claims, characterized in that the first temperature zone is operated at temperatures in the range from 50 to 200 °C, in particular in the range from 75 to 175 °C and preferably in the range from 100 to 150 °C, and/or in that the second temperature zone is operated at temperatures in the range from 100 to 500 °C, in particular in the range from 150 to 450 °C, and/or in that the third temperature zone is operated at temperatures above 400 °C, in particular above 450 °C to 500 °C, and/or in that the third temperature zone is operated at temperatures in the range from 400 to 1.200 °C, in particular in the range from 450 to 1.000 °C, preferably in the range from 500 °C to 900 °C and more preferably in the range from 550 to 850 °C.
16. The process according to one or more of the preceding claims, characterized in that the carbonized material is subsequently subjected to an activation.
17. The process according to claim 16, characterized in that the activation is similarly carried out in the carbonization apparatus or else in that the activation is carried out in a distinct apparatus and/or at different locations and/or times than the carbonization.
18. The process according to claim 16 or 17, characterized in that the activation is carried out in a conventional manner, in particular wherein the activation is carried out in the presence of customary activating gases, such as oxygen, in particular in the form of air, water vapor and/or carbon dioxide or mixtures of these activating gases, preferably in the presence of a mixture of water vapor and nitrogen, and/or in particular wherein the activation is carried out at temperatures in the range from about 700 to 1.200 °C, in particular in the range from about 800 °C to

PCT/EP 2004/008314

- 5 about 1.100 °C, preferably in the range from about 850 °C to about 1.000 °C and more preferably in the range from about 900 to about 975 °C, and/or in particular wherein the duration of the activation is in the range from about 0.5 to about 20 hours, in particular in the range from about 2 hours to about 15 hours and preferably in the range from about 5 hours to about 10 hours.
19. Activated carbon granules, in particular activated carbon spherules, obtainable by the process according to one or more of claims 1 to 18.
- 10 20. The activated carbon granules according to claim 19, characterized by an internal surface area in the range from about 800 m²/g to about 1.500 m²/g and preferably in the range from about 900 m²/g to about 1.200 m²/g, and/or by an average diameter in the range from about 0.1 mm to about 2.0 mm and preferably in the range from about 0.2 mm to about 0.8 mm with average values in the range from
15 about 0.4 mm to about 0.6 mm, and/or by a bursting pressure in the range from about 5 Newtons to about 20 Newtons per granule or spherule and/or by a riddled weight in the range from about 400 to about 800 g/l and preferably in the range from about 500 to about 750 g/l.
- 20 21. Use of activated carbon granules, in particular activated carbon spherules obtainable by the process according to one or more of claims 1 to 18 for producing adsorption materials such as adsorption (sheet) filters, filter mats, odor filters, sheet filters for protective suits, in particular for the civilian and/or military sector, filters for indoor air cleaning, gas mask filters and adsorption-capable supporting
25 structures.
22. Use of activated carbon granules, in particular activated carbon spherules, obtainable by the process according to one or more of claims 1 to 18 for protective materials, in particular protective suits against chemical poisons such as warfare
30 agents, or for filters, in particular filters for removing noxious, poisonous and/or odoriferous entities from air or gas streams.
23. Adsorption materials, in particular filters of any kind such as adsorption (sheet) filters, odor filters, sheet filters for protective suits, in particular for the civilian
35 and/or military sector, such as protective suits against chemical poisons such as warfare agents, filters for indoor air cleaning and also protective suits produced therefrom, gas mask filters, filters for removing noxious, poisonous and/or odoriferous entities from air or gas streams, filter mats and adsorption-capable supporting structures comprising activated carbon granules, in particular activated carbon
40 spherules, obtainable by the process according to one or more of claims 1 to 18.

PCT/EP 2004/008314

Abstract:

5 The invention relates to a process for producing granular, particularly spherical activated carbon by carbonization of suitable carbonaceous polymers in the form of polymer granules, in particular polymer spherules, as a starting material, which are convertible by carbonization into carbon at least essentially, wherein the polymer granules, in particular the polymer spherules, are continuously moved through a carbonization apparatus comprising a plurality of temperature zones and/or a temperature gradient so
10 that an at least essentially complete conversion of the starting material to carbon is effected.